3M Bumpon[™] Protective Products Clear Polyurethane Rollstock SJ5632 • SJ5616

Technical Data	November, 2008
Product Description	3M TM Bumpon TM Protective Products SJ5632 and SJ5616 are resilient 70 durometer clear polyurethane sheet product utilizing an aggressive acrylic-based, pressure sensitive adhesive. These products have a high strength acrylic adhesive that provides excellent shear properties at elevated temperatures. The adhesive adheres well to glass, many metal surfaces, some paints, and many high surface energy plastics (Formica®, ABS, polycarbonate, etc.). Note: This adhesive is not recommended for use on low surface energy plastics (polypropylene, polyethylene, etc.)

Construction

Bumpon protective product SJ5632	Bumpon protective product SJ5616
Clear po	olyurethane
	./ream silicone printed 3M logo.
A-20	(acrylic)
Tran	sparent
1/32 in. 0.031 in. (0.8 mm)	1/16 in. 0.062 in. (1.6 mm)
0.010 0.25	0.015 0.38
72 yds.	36 yds.
4.5 in. (114.3 mm)	4.5 in. (114.3 mm)
	.031 0.8)
	product SJ5632 Clear por White 80 lb coated paper, A-20 Tran 1/32 in. 0.031 in. (0.8 mm) 0.010 0.25 72 yds. 4.5 in. (114.3 mm) 0

*ASTM-D-D-3767 procedure A (3.2 psi) measured without liner.

Special Products of the Design-A-Bump Program

3M can customize thickness to your specifications. Call your 3M sales representative for details. Custom products require a minimum order quantity.

The thickness capability range for 3M[™] Bumpon[™] 5600 series rollstock is 1/32 in. minimum and 1/8 in. maximum.

3M[™] Bumpon[™] Protective Products Clear Polyurethane Rollstock SJ5632 • SJ5616

Typical Physical Properties and Performance	Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.			
Characteristics	Property		Test Method	Test Results
	Hardness, Shore A		ASTM-D-2240	70
	Approximate Density, lb./ft. ²	(gm/cm ³)		70 (1.1)
	Resilience, %		ASTM-D-2632	6
	Kinetic Coefficient of Friction	n*	ASTM-D-1894 Glass, Stainless Steel Formica®	> 1 > 1
	Abrasion Resistance, gm/10	000 cvcles	ASTM-C-501; Tabor H, 1 kg	0.13
	Tensile, lb./in. ² (kPa)	,	ASTM-D-412, Die A	740 (5100)
	Elongation, %		ASTM-D-412, Die A	65
	Stain Resistance		3M - 24 hrs. at 158°F against white paint, 7 days, 7 days exposed to UV	No staining
	Solvent Resistance		3M - 24 hr. immersion 5% Detergent in water 25% Detergent in water 5% Bleach in water Gasoline Motor Oil Isopropyl Alcohol	No apparent effect No apparent effect No apparent effect Slight swelling No apparent effect Slight swelling
	*Two important laws of friction applicable to 3M [™] Bumpon [™] Rollstock Protective Products are (1) friction is independent of the area of contact between solids and (2) friction is proportional to the load between solids surfaces. Thus, if the load (weight) is doubled the force required to cause surface sliding is also doubled. This is expressed mathematically as follows: Slide force = (kinetic coefficient of friction) x (weight)			
	Load Tolerance:	The "recon Protective	nmended" maximum load which 3M™ Product 5600 series rollstock will sup at 70°F (21°C) to 120°F (49°C).	
	Application Temperature:	· · ·	to 125°F (52°C)	
	Service Temperature:		C) to 150°F (66°C); 225°F (107°C) int	termittent exposure
Typical Adhesive Performance	Note: The following technical information and data should be considered represent or typical only and should not be used for specification purposes.			-
Characteristics	Static Shear Adhesive 1	Performa	nce	
	Temperature Tested at:		Time to Failure, min	utes
	75°F (24°C)		> 10,000	
	120°F (49°C)		> 10,000	
	158°F (70°C) 180°F (82°C)		> 10,000	
	180°F (82°C) > 10,000 One in. overlap shear test; ASTM-D-3654-M (1000 gram); testing completed on stainless steel test panels using 3M™ Bumpon™ Protective Product SJ5616.			
	90° Peel Adhesion Perf	•		
	Substrate		Peel Force, oz. per 1	/2 in.
	Polypropylene Polystyrene		3	
	ABS		25	
	Stainless Steel		25	
	Aluminum		25	
	Glass 3M Test Method TM-2011		25	

3M Test Method TM-2011; 72 hour dwell, 1/2 in. wide samples pulled at 12 in. per minute. Testing completed using Bumpon protective product SJ5616.

3M[™] Bumpon[™] Protective Products Clear Polyurethane Rollstock SJ5632 • SJ5616

Environmental Exposure	3M TM Bumpon TM Protective Products Clear Polyurethane Rollstock is intended for interior applications where resilience and all other physical properties will remain unchanged. When exposed to UV light for extended periods, some discoloration may occur. Bumpon clear rollstock may be used outdoors in a protected area with some discoloration possible. Simultaneous exposure to high humidity and temperature may degrade (soften) the product composition.			
Features	• Transparent – universal color match.			
	• Excellent resistance to yellowing.			
	• Can be die cut to a variety of shapes and sizes.			
	• Excellent resistance (Resulting from a urethane composition which contains no plasticizers.) to marring or staining.			
	• Long aging resiliency – will not crack or harden.			
	Excellent cushioning properties.			
	• Excellent abrasion resistance.			
	• Vibration and shock damping.			
	• Easy application – pressure sensitive adhesive backing.			
Application Ideas	 Die cut shapes for glass table tops, cushioning glass from metal and wood frames. Die cut shapes for use as cushions and spacers on cabinet doors, drawers, and lids. Die cut shapes for use as skid-resistant feet on small appliances and desk top 			
	equipment.			
	• Die cut shapes for use as cushions and pads on glass or clear plastic shelves.			
	• Strips or pads for use as skid-resistant surfaces on glass or clear plastic shelves.			
	• Antichafe protection.			
	Corner protection strips.			
	Door kick pads.			
Application Techniques	To obtain maximum adhesion, surfaces must be unified, dry, and free of contaminants. Surface contact is fundamental to adhesive performance. To maximize contact on a substrate:			
	• Clean surfaces with low strength solvents such as isopropyl alcohol (rubbing alcohol) or heptane.			
	Note: Be sure to follow the solvent's manufacturer's precautions and directions for use when using solvents.			
	• Apply firm pressure to increase the cold flow and contact of the adhesive with the substrate.			
	• Allow time (dwell) to increase the surface contact and adhesion.			
	Note: Product selection is ultimately the user's responsibility. Users should conduct their own tests under actual use and storage conditions to determine whether the product is fit for a particular purpose and method of application.			

3MTM BumponTM Protective Products Clear Polyurethane Rollstock

SJ5632 • SJ5616

Storage	Store in original cartons at 60-80°F (16-27°C) and 40-50% relative humidity.
Shelf Life	To obtain best performance, use this product within 18 months from date of manufacture.
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
Warranty, Limited Remedy, and Disclaimer	Many factors beyond 3M's control and uniquely with user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

3M

Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue St. Paul, MN 55144-1000 800-362-3550 • 877-369-2923 (fax) www.3M.com/industrial



Recycled Paper 40% pre-consumer 10% post-consumer

3M and Bumpon are trademarks of 3M Company. Formica is a registered trademark of Formica Corporation. Printed in U.S.A. ©3M 2008 70-0709-1085-9 (11/08)